



grafo lit

Grafo Lit d.o.o.
SI-3310 Žalec
Vrbje 80a, Slovenija
Tel.: +386 (0)3 713 68 22
Fax: +386 (0)3 713 68 30
www.grafolit.si

ROYAL WHITE

- Nepremazan papir, izdelan iz 100% beljenih E.C.F. vlaknin izdelanih iz dreves, katerih proizvajalci izpolnjujejo metode in politiko za zagotavljanje trajnostnega upravljanja z gozdovi.
- Ta izdelek je brez kislin, z alkalno rezervo.
- Optimalni razred beline.
- Dobre kakovosti.
- Visoki rezultati za odlične kopije.
- Primeren za fotokopiranje, laserski tisk, ink jet in fax.

- Uncoated paper, made with 100% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest.
- The product is Acid Free, with alkaline reserve, guaranteeing long life according to ISO 9706.
- High grade of white.
- Optimum quality.
- High performance for perfect copies.
- Suitable for photocopying, laser printing, ink-jet and faxing.

PARAMETER	ENOTA Jedinica Einheit Unit	VREDNOST Vrijednost Zielwert Target	ODSTOPANJE Odstupanje Toleranz Tolerance	Standard
Gramatura / Gramatura Flächengewicht / Grammage	g/m ²	80	± 4%	ISO 536
Debelina / Debljina Dicke / Thickness	g/m ²	104	± 4%	ISO 534
Gladkost Bekk / Glatkoća Bekk Glatte Bekk / Smoothness Bekk	s	20	± 10	ISO 5627
Belina / Bjelina Weissgrad / Brightness R 457 nm	%	103	± 1	ISO 2470
Belina CIE / Bjelina CIE Weissgrad CIE / Whiteness CIE		146	- 3%	ISO 11475
Opaciteta / Opacitet Opazität / Opacity	%	93	MIN	ISO 2471
Utržna odpornost / Čvrstoča Zugfestigkeit / Tensile s.	kN/m MD CD	2,7 1,3	MIN	ISO 1924-2
Togost Taber / Krutost po Taberu Steifigkeit Taber / Stiffness Taber	mNm MD CD	0,18 0,08		TAPPI 489